



Ti-Pure™

R-960 Titanium Dioxide

Product Information

Product Description

Ti-Pure™ R-960 is a rutile titanium dioxide pigment manufactured by the chloride process. It is excellent for exterior plastic applications that require outstanding chalking resistance and gloss, tint, and physical property retention. The grade is a fine, dry, white powder with typical properties as shown in **Table 1**.

Table 1. Physical Properties


Titanium Dioxide, wt%, min.	89
Alumina, wt%, max.	3.5
Amorphous Silica, wt%, max.	6.5
Organic Treatment	None
Specific Gravity	3.9
pH	7.4
Resistance (aqueous slurry), k ohm-cm, min.	4

Suggestions for Use

Ti-Pure™ R-960 is designed primarily for exterior color durable applications. The surface treatment of Ti-Pure™ R-960 minimizes potential reaction with polymer resins and additives, while continuing to provide the high level of UV radiation protection associated with rutile titanium dioxide. In tinted exterior applications, the lower opacity strength of Ti-Pure™ R-960 actually minimizes the total colorant cost at the desired level of UV protection.

Rutile titanium dioxide is an efficient UV radiation protector for plastic applications because it strongly absorbs radiation below 380 nm. Rutile titanium dioxide,

Figure 1. Optical Properties



in the presence of water and oxygen, may then act as a photocatalytic agent. Ti-Pure™ R-960 is surface coated with silica to minimize this photocatalytic potential. An additional alumina treatment improves dry bulk conveying and dispersibility.

Table 2. General Properties

Opacity Strength	Low
Undertone Tint	Cream
Dispersibility in:	
Plasticized Vinyl	Good
Plasticizers	Good
Dry Blending Operations	Good
Melt Compounding	Good
Chalking Resistance	Excellent

Ti-Pure™ R-960 provides maximum surface retention while still providing efficient UV radiation protection. **Figures 2 and 3** demonstrate the improved gloss retention of R-960 in plastics, compared to grades Ti-Pure™ R-101 and Ti-Pure™ R-103.

The surface treatments used to optimize Ti-Pure™ R-960 outdoor performance are hygroscopic. Moisture absorbed during shipping and storage can affect film integrity at very high TiO₂ loadings and temperatures. As **Figure 4** shows, Ti-Pure™ R-960 must be evaluated carefully for film applications. For applications requiring less moisture, Ti-Pure™ R-105 is recommended.

Figure 2. Gloss Retention of Polypropylene, Xenon Exposure




Figure 3. Gloss Retention of PVC, Florida Exposure 45° South





Figure 4. Lacing Resistance versus Temperature, Ti-Pure™ R-960



15% TiO₂ in low density polyethylene. Extruded at temperatures shown, 1.5-2 mil thick.

Shipping Containers

Ti-Pure™ R-960 rutile titanium dioxide is available in a range of packaging to meet your needs:

- 25 kg multi-ply paper bags
- 1 metric ton (1,000 kg) flexible intermediate bulk containers

For further information about this grade or to request a sample, please see the Ti-Pure™ web site.

CAUTION: Do not use or resell Chemours™ materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. These products may not be directly added to food, pharmaceuticals, cosmetics, or cigarette papers/filters for tobacco products.

For medical emergencies, spills, or other critical situations, call (844) 773-2436 within the United States. For those outside of the United States, call (302) 773-1000. The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit tipure.com

© 2020 The Chemours Company FC, LLC. Ti-Pure™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

C-10422-2 (2/20)